


D 263® T eco Thin Glass

D 263® T eco thin glass is a clear borosilicate glass that has a high chemical resistance and is produced by the down-draw method. It is available in a variety of thicknesses ranging from 0.03 mm to 1.1 mm. D 263® T eco borosilicate glass is available in standard stock size sheets or can be custom cut into round or square shapes. D 263® T eco thin glass is used as a substrate glass for coatings or replacement for plastic for applications in the automotive and electronics industries. D 263® T eco is manufactured without adding arsenic and antimony as refining agents.



Applications




Resistive touch panel for built-in car navigation

- Stable against sunlight and heat
- Not permeable to humidity
- Flexibility is similar to that of plastic
- Easy to cut by laser or scribe and break method

Optocaps in laser diodes

- High luminous transmittance
- Easy to process
- Coefficient of thermal expansion match with metals for hermetic sealings



Substrate glass for IR cut-off filter for camera modules in mobile phones

- High luminous transmittance
- Easy to dice by diamond saw
- Coatings adhere well due to excellent surface quality
- Smooth surface for coatings without previous polishing
- Range of thin thicknesses enables easy adaptation for future product miniaturization

Technical Data

Dimensions	440 mm x 360 mm (17.3 in x 14.2 in), other sizes on request
Thicknesses	0.03 mm up to 1.1 mm
Luminous transmittance T_{VD65} (d = 1.1 mm)	91.7 %
Coefficient of mean linear thermal expansion α (20 °C; 300 °C) (static measurement)	$7.2 \cdot 10^{-6} \text{ K}^{-1}$
Transformation temperature T_g	557 °C
Dielectric constant ϵ_r at 1MHz	6.7
Refractive index n_D	1.5230
Density ρ (annealed at 40 °C/h)	2.51 g/cm ³

Advanced Materials
SCHOTT North America, Inc.
555 Taxter Rd
Elmsford, NY 10523
USA

Phone: +1 914 831-2200
Fax: +1 914 831-2201
info@us.schott.com
www.us.schott.com

SCHOTT
glass made of ideas